

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 December 2000 (07.12.2000)

PCT

(10) International Publication Number
WO 00/73576 A1

(51) International Patent Classification⁷: D21C 9/10, D21H 23/04 // 21:32, 17:65

(21) International Application Number: PCT/EP00/04610

(22) International Filing Date: 18 May 2000 (18.05.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
991241 1 June 1999 (01.06.1999) FI

(71) Applicant (*for all designated States except US*): AGA AK-TIEBOLAG [SE/SE]; Lidingö, S-181 81 Lidingö (SE).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): TIGERSTRÖM, Anna [SE/SE]; Tjärhovsgatan 5, 3 tr, S-116 21 Stockholm (SE).

(74) Agent: BORENIUS & CO OY AB; Kansakoulukuja 3, FIN-00100 Helsinki (FI).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— With international search report.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: BLEACHING OF LIGNIN AND PROCESS FOR PRODUCING PAPER

(57) Abstract: The present invention relates to the bleaching of lignin present in pulp fibers in an aqueous environment such as a pulp suspension. The invention also relates to a process for producing paper or board from pulp containing such bleached lignin. According to the invention carbon dioxide is used for the bleaching of lignin.

WO 00/73576 A1

Bleaching of lignin and process for producing paper

The present invention relates to the bleaching of lignin present in pulp fibers in an aqueous environment such as a pulp suspension. The invention also relates to a process for producing paper or board from pulp containing such bleached lignin.

Lignin is an amorphous polymer which, like a glue, keeps the cellulose fibers together in wood. Some lignin also exist in the fiber wall. In its native state in wood lignin is of light color.

The purpose of chemical pulping, such as kraft pulping, is to dissolve the lignin from the wood matrix with a cooking liquor. During cooking lignin is broken down into smaller units and becomes darker, i.e. increases the light absorption. The dark lignin components, some of which are dissolved and some of which are still in the fiber, give the pulp a dark colour.

In the production of paper or board a large proportion of the lignin is washed off the fibers in one or more washing steps. According to EP 296198 (AGA Aktiebolag) the washing-out of substances which contribute to the chemical oxygen demand (COD) in an alkaline cellulosic pulp is improved if the pH of the wash water is lowered with an acid such as carbon dioxide. According to an article by Östberg, G., 5th International Conference of New Available Technique, The World Pulp and Paper Week, June 4-7, 1996, Stockholm pp. 508-515, the said improved washing results in an increased degree of delignification and a consequent decrease in the consumption of bleaching chemicals. Calcium carbonate is formed in a reaction between calcium and the carbonate ions generated by the carbon dioxide. No increase of calcium carbonate deposition on the equipment was observed.

Sundin, J. et al. in "Precipitation of lignin during pulp washing", p. 219-227, proceedings, TAPPI Pulping Conference, 1998, discloses that the addition of calcium or magnesium ions to deionized water used for washing a pulp provided washed pulps with a higher kappa number (a common measure of the lignin content) than pulps washed without addition of these ions. There was found to be a correlation between kappa number and the concentration of calcium, magnesium and the like ions in the wash water. The more ions were added, the higher the kappa number.

Sundin et al. also showed that lignin which precipitated during washing with water to which calcium ions had been added was darker than the other residual lignin in the pulp. Pulps washed with water containing calcium ions were significantly darker than those without such ions.

In a recent publication Gustavsson, C. et al. Nordic Pulp and Paper Research Journal Vol 14, No 1, 1999, p 71-81, noted a distinct decrease in the content of calcium when cooking with a high hydroxide ion concentration. An explanation to the phenomenon is said to be that the calcium is bound to dissolved lignin fragments at high hydroxide ion concentration and, consequently, there is a decreased precipitation of calcium carbonate on the pulp fibers.


On the other hand, WO 90/09483 (Mo och Domsjö Aktiebolag) utilizes the tendency of calcium carbonate to precipitate at an alkaline pH for reducing the amount of gypsum (calcium sulphate) precipitation in a paper stock. A precipitation of the calcium carbonate is induced by adding (bi)carbonate ions to the system. The ions may be created *in situ* by an addition of sodium hydroxide and carbon dioxide.

According to WO 99/00545 (Sunds Defibrator Industries AB) the release of calcium ions into the filtrate of a papermaking system by acidic bleaching conditions below pH 7 cause harmful precipitations on the equipment. The calcium ions are absorbed on the pulp by an addition of carbonate ions and removed with the pulp

According to US 5,139,613 (Canadian Liquid Air Limited) carbon dioxide is used to acidify a pulp slurry after it has been bleached with hypochlorite or hydrogen peroxide. The souring with CO₂ instead of SO₂ does not destroy the bleaching chemical which allows the residual bleaching chemicals to continue their bleaching effect for a longer time.


According to GB Patent Application 2 008 562 carbon dioxide may be used for increasing the solubility of calcium carbonate and for the hardening of recycled waters used in the treatment of pulp from waste paper.

Carbon dioxide is a gas, which easily dissolves under alkaline conditions, e.g. in water or a pulp suspension forming carbonic acid and bicarbonate and/or carbonate ions according to the reaction:



Water soluble salts of carbonic acid such as sodium bicarbonate NaHCO_3 and sodium carbonate Na_2CO_3 also provide bicarbonate and carbonate ions in an aqueous environment.

Carbonate ions have the ability of being bound to calcium ions and of creating calcium carbonate, which is a salt with a low solubility at alkaline pH:



At a pH below about 8 calcium carbonate starts to dissolve and the concentration of free calcium ions increases. High concentrations of free calcium ions in a papermaking system are known to cause complex coagulation and scaling problems in papermaking.


The present invention, as defined in the appended claims, is based on the realization that carbonic acid and salts thereof, which provide carbonate and bicarbonate ions, can be used for bleaching calcium containing lignin dissolved or present in pulp fibers in an aqueous pulp suspension.

Although not wishing to be bound by any theory, it is believed that the (bi)carbonate ions are capable of trapping calcium present in the system and thus reducing the influence of calcium on the lignin. This, in turn, provides lignin compounds in the pulp which are lighter in colour. The bleached lignin compounds may also be easier to remove from the fibers causing the pulp to have a reduced lignin content. In either case, the paper resulting from the (bi)carbonate bleached pulp will have an increased brightness. Thus, such a pulp requires a reduced amount of other bleaching chemicals to provide the desired brightness.

The carbonic acid is preferably provided by dissolving carbon dioxide gas in the aqueous pulp suspension. The dissolved gas will produce carbonic acid in the water and will, in turn, provide carbonate and/or bicarbonate ions in the suspension. Carbon dioxide may also be added in liquid or solid form to the suspension.

The carbonates/bicarbonates in the aqueous environment will associate with calcium ions in said environment in such a way that the calcium ions become "trapped" in calcium carbonate. This will reduce the amount of calcium available to influence the lignin. The

result will show up as an increased brightness and possibly also as a lower kappa number in the pulp:



For a high kappa pulp intended to be used in its unbleached form, for example in packaging grades such as linerboard and sack paper, the result of carbon dioxide addition and consequent calcium ion removal from lignin is a brighter pulp/paper with very likely also a lower kappa number at the same cooking conditions. This pulp/paper can be used as such as an unbleached product with higher brightness or the product may provide savings in the top layer of bleached fiber and coating added for optical/printing purposes. The lignin bleaching effect can also be utilized for producing a pulp with the same kappa number as before but with less severe cooking conditions, which means increased productivity, steam savings, increased selectivity or savings in cooking chemicals.

For a pulp intended to be bleached, reducing the influence of calcium ions on lignin makes a pulp with a improved bleachability; consuming less bleaching chemicals to a given brightness.

To reach the desired effect, the carbon dioxide may be added at various positions in the fiber line or the papermachine. It should be observed that the (bi)carbonate ions required in the bleaching process may also be provided by adding carbonic acid or salts of carbonic acid, i.e. (bi)carbonate salts such as sodium bicarbonate or carbonate to the pulp suspension.

The preferred way of providing the carbonate/bicarbonate ions is to add carbon dioxide gas to the aqueous pulp suspension. From a dissolving point of view of the carbon dioxide should preferably be added to an aqueous medium in an alkaline state. Thus, a pH around 8 or above is preferred. On the other hand, the value of inactivating deleterious calcium ions in lignin is highest at a lower pH when less phenolic groups are ionized and the lignin molecules have a higher tendency to precipitate. The pH decreasing effect of the addition of carbon dioxide may be countered by the addition of an alkali such as sodium hydroxide to the solution.

The optimum pH at which to add CO₂ depends on the number of groups in the lignin with the capacity to become ionized (normally a function of kappa number, cooking method, wood type), the purity of the cooking chemicals and water purity. As the lignin which is most difficult to remove is left in the pulp to the last bleaching stage and its number of ionized groups is low, CO₂ addition before such stage to trap any calcium ions present, can be especially beneficial.

One should avoid adding CO₂ when a high amount of the black liquor is present. A publication by Hartler ("Sorption cooking", Svensk Papperstidning, p 457-463, No 14, 1978) describes sorption cooking, a method where CO₂ addition increases yield by re-deposition of lignin from the black liquor to the fiber. Using the same chemical (CO₂) sorption cooking has quite the opposite effect to the process described in this patent application.

In the case of a high kappa pulp one suitable location to add CO₂ is to the outlet of final storage in the pulp mill from where the pulp is transported to storage in the paper mill. CO₂ can either be added to the dilution water or directly to the pulp.

The pulp is preferably a chemical pulp. The pulp may or may not be delignified in an oxygen delignification stage. One preferred stage of adding CO₂ is before a D-stage bleaching, preferably before a storage tower before such bleaching. The CO₂ may also be added to a pulp which is subsequently to be bleached with chlorine dioxide, peroxide, peracetic acid, ozone, chlorine, hypo, or the like bleaching chemical. Another preferred position is before, after or in a wash stage in the fiber line of a pulp mill. Adding bleaching CO₂ after a wash stage wherein a large proportion of the lignin has been removed by washing is especially effective.

In a preferred embodiment of the invention the pulp is a chemical pulp which has been washed and carbon dioxide is fed into a stream of pulp between a wash stage and a storage at the end of the fiber line of a pulp mill. The carbon dioxide is preferably fed into a stream of water used to dilute the pulp prior to final storage in the fiber line.

The calcium trapped by said carbon dioxide from said lignin may be removed from said pulp suspension by a press stage or a wash stage preceding storage or the like process.

The pulp to be treated according to the present invention may also be a papermaking stock before, after or in a stock preparation stage of a paper mill. Examples of such stock preparation stages are a dilution stage, a refining stage, a screening stage and a mixing stage.

The carbon dioxide may be introduced into a stream of white water in the long or the short circulation of a papermachine.

The present invention is preferably utilized in the production of paper or board whereby paper or board is produced having an increased brightness and/or a reduced kappa number, compared to paper or board produced without the (bi)carbonate addition, by a process comprising

- providing a chemical pulp suspension of cellulosic fibers and calcium containing lignin compounds in an aqueous environment,
- providing carbonic acid or a salt thereof in said suspension or in a stream of water entering said suspension for causing a substantial bleaching of lignin present in said suspension and/or for facilitating the freeing of calcium containing lignin from the fibers in said suspension,
- processing said suspension into paper or board.

The lignin which is bleached by the present process is generally a calcium-containing lignin and the amount of carbon dioxide or carbonic acid salt added to the suspension should be sufficient to trap a significant amount of the calcium present in the suspension, thus providing a lighter coloured lignin which will also more easily be freed from the fibers.

The following examples illustrate the invention:

Example 1

CO₂ was added to a high kappa pulp at the outlet from the final storage in a pulp mill from where the pulp was transported to storage in the paper mill. The CO₂ was added to the dilution water and the brightness of the final product, the paper, became 2 ISO units brighter.

Example 2

In a case of a softwood kraft pulp to be bleached with chlorine dioxide, 3 kg CO₂/ton of pulp was added before 30 minutes storage after which the pulp was pumped to the chlorine dioxide bleaching stage. 3 kg CO₂/ton of pulp addition resulted in 3 kg ClO₂/ton of pulp savings in the bleach plant to reach the same bleach result.

Example 3

In a case of kraft pulp to be bleached in a TCF sequence with peroxide 4 kg CO₂/ton of pulp was charged to the dilution water of the pulp before the final wash stage before bleaching. In the bleach plant the bleach chemical consumption was reduced with 5 kg H₂O₂/ton pulp.

Example 4

A laboratory test was performed in a Quantum mixer. A softwood kraft pulp with kappa number 65 was used. The pulp was diluted with de-ionized water to a consistency of 8 %. CO₂ gas was added to the pulp in the mixer under slow stirring. The pH was observed during 60 minutes treatment.

Thereafter the pulp was diluted with de-ionized water to a consistency of 1 %. The pulp suspension was divided in two samples, where one was adjusted to pH 5 with H₂SO₄. Sheets were prepared and the brightness was measured with an Elrepho instrument. The results of the trials is shown in the Table below.

Table

Trial No.	CO ₂ kg/t	pH after 60 min.	Adjusted pH	Brightness % ISO	Unadjusted pH	Brightness %
4	0	8.2	5	19.8		
3	0	8.2			9.2	18.4
6	3	6.8	5	20.2		
5	3	6.8			8.5	19.3
8	9	6	5	20		
7	9	6			7.6	19.4
1	15	6.2	5	21.6		
2	15	6.2			7.1	20.8

The tests clearly show an increased brightness in response to an increased addition of carbon dioxide.

Claims

1. Use of carbonic acid or a salt thereof for the bleaching of calcium containing lignin present in pulp fibers in an aqueous environment such as a pulp suspension.
2. The use according to claim 1 wherein said carbonic acid is provided by dissolving gaseous carbon dioxide in said aqueous environment, said carbonic acid dissociating in said aqueous environment and providing carbonate and/or bicarbonate ions.
3. The use according to claim 1 or 2 wherein the pH lowering effect of the carbonic acid is countered by the addition of an alkali such as sodium hydroxide to the aqueous environment.
4. The use according to claim 1 wherein a salt of carbonic acid such as sodium bicarbonate or sodium carbonate is dissolved into said aqueous environment for provided carbonate and/or bicarbonate ions.
5. The use according to any one of the preceding claims 1 to 4 wherein said aqueous environment is an aqueous pulp suspension or a filtrate from a dewatering stage.
6. The use according to claim 5 wherein said aqueous environment is a chemical pulp.
7. The use according to claim 6 wherein said chemical pulp is an unbleached or a semi-bleached pulp.
8. The use according to claim 6 wherein said chemical pulp is an unbleached pulp before, after or in a wash stage of a fiber line of a pulp mill.
9. The use according to claim 8 wherein said chemical pulp is an unbleached pulp just after a wash stage of a fiber line of a pulp mill.
10. The use according to claim 6 wherein said chemical pulp is a washed chemical pulp and carbon dioxide is fed into a stream of pulp between a wash stage and a storage at the end of the fiber line of a cellulose mill.
11. The use according to claim 6 wherein carbon dioxide is fed into a stream of water used to dilute the pulp just before or just after final storage of the fiber line.

12. The use according to claim 1 wherein calcium is trapped by carbonate or bicarbonate ions provided by said carbonic acid or its salt thereby reducing the influence of calcium on said lignin and facilitating the bleaching of lignin and/or freeing of lignin from fibers in said pulp suspension.

13. The use according to claim 6 wherein said chemical pulp is a pulp which has been bleached in an oxygen delignification step.

14. The use according to claim 6 wherein said chemical pulp is a pulp which is subsequently to be bleached with chlorine dioxide, peroxide, peracetic acid, ozone, chlorine, hypo, or the like bleaching chemical.

15. The use according to claim 14 wherein carbon dioxide is fed into a pulp added before, in or after a storage tower or to a dilution water added to said pulp before, in or after a storage tower preceding a chlorine dioxide bleaching stage in a fiber line of a cellulose mill.

16. The use according to claim 1 wherein said pulp is a papermaking stock before, after or in a stock preparation stage of a paper machine.

17. The use according to claim 16 wherein said stock preparation stage is a dilution stage, a refining stage, a screening stage or a mixing stage.

18. The use according to claim 16 wherein said carbon dioxide is introduced into a stream of white water in the long or the short circulation of a papermachine.

19. A process for producing paper or board comprising

- providing a chemical pulp suspension of cellulosic fibers and calcium containing lignin compounds in an aqueous environment,
- providing carbonic acid or a salt thereof in said suspension or in a stream of water entering said suspension for causing a substantial bleaching of said calcium containing lignin present in said suspension and/or for facilitating the freeing of lignin from the fibers in said suspension,
- processing said suspension into paper or board having an increased brightness and/or a reduced kappa number compared to a similar product produced without said carbonic acid or its salt.

20. The process according to claim 19, wherein said carbonic acid is provided by the introduction of carbon dioxide gas into said suspension or stream.

21. The process according to claim 19 or 20, wherein carbonic acid and/or an alkaline metal salt thereof is introduced in said suspension or in a stream of water entering said suspension in an amount sufficient for providing a chemically effective amount of carbonate and/or bicarbonate ions in said suspension for trapping a substantial amount of the calcium and reducing the amount of calcium influencing the lignin.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 00/04610

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D21C9/10 D21H23/04 //D21H21:32,D21H17:65

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21C D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 016 029 A (SAMUELSON HANS OLOF) 5 April 1977 (1977-04-05) abstract column 5, line 57 -column 6, line 14 ----	1-7
X	WO 88 04705 A (AGA AB) 30 June 1988 (1988-06-30) abstract claims 2,3,8; figure 2 & EP 0 296 198 B (AGA AB) cited in the application ----	1-12, 16-21
X	EP 0 884 416 A (PRAXAIR TECHNOLOGY INC) 16 December 1998 (1998-12-16) page 4, line 18 - line 35 figure ----- -/--	1-12, 16-21

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

14 July 2000

Date of mailing of the international search report

20/07/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Naeslund, P

INTERNATIONAL SEARCH REPORT

Intern. Appl. No.

PCT/EP 00/04610

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 99 35333 A (LAURILA LUMME AULI ;LEINO HANNU JUHANI (FI); PAKARINEN HEIKKI (FI)) 15 July 1999 (1999-07-15) abstract; claims 1,4,5 ---	1-12, 16-21
X	US 5 139 613 A (LACHAPELLE RAYMOND C) 18 August 1992 (1992-08-18) cited in the application the whole document ---	1-12
A	WO 97 30208 A (KEMIRA CHEMICALS OY ;RENVALL ILKKA (FI); AKSELA REIJO (FI); PAREN) 21 August 1997 (1997-08-21) claims 1-16 ---	1-21
X	GB 815 247 A (COLUMBIA CELLULOSE COMPANY, LIMITED) 24 June 1959 (1959-06-24) the whole document ---	1-12
A	EP 0 899 374 A (OJI PAPER CO) 3 March 1999 (1999-03-03) claims 1-8 ---	1-21
X	WO 90 09483 A (MO OCH DOMSJÖ AB) 23 August 1990 (1990-08-23) the whole document ---	1-12, 16-21
X	US 5 378 322 A (HORNSEY DEREK) 3 January 1995 (1995-01-03) abstract; claims ---	1-12, 16-21
X	WO 99 24661 A (LEINO HANNU JUHANI ;AGA AB (SE); HOLMBERG ANNA LINNEA (SE)) 20 May 1999 (1999-05-20) examples 1-3 ---	1-12, 16-21
X	EP 0 281 273 A (BOC GROUP INC) 7 September 1988 (1988-09-07) abstract; claims -----	1-12, 16-21

INTERNATIONAL SEARCH REPORT

Intern. Application No

PCT/EP 00/04610

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4016029	A	05-04-1977	SE 393138 B	02-05-1977
			AT 345659 B	25-09-1978
			AT 178975 A	15-01-1978
			BR 7501340 A	09-12-1975
			CA 1036757 A	22-08-1978
			CH 591596 A	30-09-1977
			DE 2509691 A	25-09-1975
			FI 750636 A	15-09-1975
			FR 2264126 A	10-10-1975
			GB 1496537 A	30-12-1977
			IT 1030235 B	30-03-1979
			JP 911319 C	21-06-1978
			JP 50121503 A	23-09-1975
			JP 52028884 B	29-07-1977
			NO 750745 A,B,	16-09-1975
			SE 7403452 A	15-09-1975
			SU 847933 A	15-07-1981
			ZA 7501267 A	28-01-1976
WO 8804705	A	30-06-1988	AT 67536 T	15-10-1991
			AU 1082688 A	15-07-1988
			AU 7352587 A	15-07-1988
			BR 8707606 A	03-10-1989
			CA 1286454 A	23-07-1991
			DE 3773204 D	24-10-1991
			EP 0296198 A	28-12-1988
			ES 2003282 A	16-10-1988
			FI 883851 A,B,	19-08-1988
			JP 7078315 B	23-08-1995
			JP 1502917 T	05-10-1989
			MX 167744 B	12-04-1993
			NO 172550 C	15-11-1994
			NZ 220101 A	26-04-1989
			PT 84777 A,B	01-05-1987
			SE 8605510 A	17-09-1987
			WO 8804706 A	30-06-1988
			US 5429717 A	04-07-1995
EP 0884416	A	16-12-1998	BR 9801811 A	28-09-1999
			CA 2240031 A	10-12-1998
			CN 1214388 A	21-04-1999
WO 9935333	A	15-07-1999	FI 103520 B	15-07-1999
			AU 2627099 A	20-09-1999
			AU 7921598 A	26-07-1999
			EP 0981665 A	01-03-2000
			EP 0986671 A	22-03-2000
			WO 9945202 A	10-09-1999
US 5139613	A	18-08-1992	NONE	
WO 9730208	A	21-08-1997	FI 960756 A	20-08-1997
			AU 1797397 A	02-09-1997
			EP 0882151 A	09-12-1998
GB 815247	A		NONE	
EP 0899374	A	03-03-1999	JP 11081173 A	26-03-1999

INTERNATIONAL SEARCH REPORT

Internat. Application No

PCT/EP 00/04610

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0899374 A		CA 2246107 A	01-03-1999
WO 9009483 A	23-08-1990	SE 461860 B	02-04-1990
		AT 135769 T	15-04-1996
		AU 637082 B	20-05-1993
		AU 5084490 A	05-09-1990
		CA 2046285 A,C	14-08-1990
		DE 69026078 D	25-04-1996
		DE 69026078 T	05-09-1996
		EP 0457822 A	27-11-1991
		ES 2084690 T	16-05-1996
		FI 96336 B	29-02-1996
		JP 2840982 B	24-12-1998
		NO 173561 C	29-12-1993
		US 5262006 A	16-11-1993
US 5378322 A	03-01-1995	CA 2069713 A	28-11-1993
		DE 69315119 D	18-12-1997
		DE 69315119 T	05-03-1998
		EP 0572304 A	01-12-1993
		ES 2108839 T	01-01-1998
		FI 932435 A	28-11-1993
		JP 6299496 A	25-10-1994
WO 9924661 A	20-05-1999	FI 974145 A	06-05-1999
		AU 1034199 A	31-05-1999
EP 0281273 A	07-09-1988	AT 91734 T	15-08-1993
		AU 1175188 A	01-09-1988
		DE 3882395 D	26-08-1993
		DE 3882395 T	02-12-1993
		FI 880918 A	28-08-1988
		JP 1045887 A	20-02-1989
		JP 2582838 B	19-02-1997
		NO 880763 A	29-08-1988
		ZA 8800945 A	22-02-1989